















Format [mm]		Trendtime 3	Trendtime 4	Trendtime 8*1	
Top layer		570 x 95 x 10,5	2010* x 160 x 13	1882* x 190 x 15	1882* x 190 x 14
Packaging		≥ 2,5 mm	ca. 3,6 mm	ca. 4,0 mm	ca. 3,0 mm
Packaging	Pack: m ² /kg	20 Elements	9 Elements	8 Elements	9 Elements
	Pallet: m ² /kg	1,083 / 5,40	2,894 / 19,40	2,861 / 23,464	3,218 / 26,397
		36 Packs	32 Packs	32 Packs	32 Packs
		38,99 / 194,40	92,621 / 620,64	91,546 / 750,848	102,976 / 844,704
Guarantee (according to Parador guarantee conditions)			25 years (private use) 10 years (commercial use)	Notes	*1 joint length permitted per package - cleaning and maintenance see instructions - technical changes reserved

*1 For Trendtime 8 Multiplank (# 1744429): The bevel size between the individual lamellas on a plank can vary.

Product labelling	Tolerances (EN 13489)	
        	Admissible difference in length (± 0.1 %)	± 0,05%
	Admissible difference in width (± 0.2 mm)	± 0,1 mm
	Squareness of the element (≤ 0.2 %)	≤ 0,05 %
	Longitudinal curvature along the element (≤ 0.1 %)	≤ 0,05 %
	Transverse curvature across the width (≤ 0.2 %)	≤ 0,08 %
	Height differences of elements (≤ 0.2 mm)	≤ 0,18 mm
	Moisture content at the time of first delivery (5-9%)	6 - 8 %

*not valid for smoked products.

Classification general product features		
	Test method	Rating
 Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat
 Effect of a furniture leg	EN 424	No visible changes
 Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN ISO 10456	Trendtime 3: 0,070 m ² K/W Trendtime 4: 0,087 m ² K/W Trendtime 8: 0,100 m ² K/W
 Formaldehyde (E1 = 0,1 ppm)	EN 16516	≤ 0,05 ppm
 Acoustical - Impact noise reduction	ISO 717-2	Trendtime 3: - only suitable for all-over adhesion Trendtime 4 / 8: 18 dB (with Akustik-Protect 100)
Disposal	EAK-Code-number	20 01 38

Classification surface characteristics				
	Test method	Rating		
		Natural oiled plus	Natural oiled plus (rough sawn)	Lacquer
 Slip resistance	EN 13893	μ ≥ 0,49	μ ≥ 0,53	μ ≥ 0,47
	CEN/TS 15676	99 (USRV)	99 (USRV)	29 SRT (SRV wet) 51 SRT (SRV dry)
 Reaction to fire, click-installation as a floating floor Reaction to fire, installation by all-over adhesion	EN 13501-1	D _f s1		
 Chemical resistance	EN 13442:2023 Annex B	Category 5	Category 5	Category 5
Bond strength / Cross cutting test	ISO 2409	n.n.	n.n.	Category 0
Slip resistance, inclined plane	EN 16165, Annex B	R 10	R 10	R 9

Changed:	QMB	File name:	PA_TDS_Parkett_Trendtime_EN_20231201
Date:	01.05.2013	Latest update at	https://parador.de/en/pcms/downloads/downloadfile/file_id/216/
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.12.2023

Free sorting according to EN 13489					
Assortment:	Wide plank				
Characteristics according to EN 1310:	Upper side of the plank				
Design:	Trendtime 3		Trendtime 4		Trendtime 8
Type of wood:	Oak		Oak		Oak
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE		Quercus petraea Liebl., Quercus robur L. / QCXE		Quercus spp. / QCXE
Shortcut / sorting (internal):	TT3-GÜ		ES-LH-TT4-EI		ER-TT8-EI
	Version 4 2023		Version 12 2016		Version 4 2015
Grade:	Living	Living Plus	Living	Rustikal	Classic
Sound sapwood	permitted	not permitted	permitted	not permitted	permitted
Knot (intergrown)	permitted: up to 30 mm		permitted: up to 50 mm	permitted: up to 80 mm	permitted
Falling out knot	permitted: up to 10 mm		permitted: up to 25 mm	permitted: up to 60 mm	permitted
Pinkknots	permitted		permitted: cluster of knots		permitted
Filling	permitted				
Slight cracks / hairline cracks	permitted				
Bark pocket	not permitted			permitted	not permitted
Lightning cracks	permitted				
Slope of grain	no criterion				
Healthy heart	-		not permitted	permitted	
Medullary ray	permitted				
Discoloration, colour variation	permitted: all brown colours		permitted: slight colour variations	permitted: all colours	
White streaks	permitted				
Pilling sticks marking	not permitted				
Biodeterioration (EN 1311)	not permitted				
Non-visible parts					
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.					
Comment					
Maximum 3% of planks are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.					

Changed:	QMB	File name:	PA_TDS_Parkett_Trendtime_Anhang_EN_20231201		
Date:	01.03.2013	Update:	https://parador.de/en/pcms/downloads/downloadfile/file_id/216/		
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.12.2023		Page 1 of 1